

## Declaration of Performance

1. Ref. no	PM – 005 – 2018
2. Type	Laminated veneer lumber made from beech
3. Purpose	Laminated veneer lumber according to EN 14374:2005-02 for non-load bearing, load bearing and stiffening elements
4. Trade name	Board BauBuche S Board BauBuche Q
Manufacturer	Pollmeier Furnierwerkstoffe GmbH Pferdsdorfer Weg 6 D-99831 Creuzburg
5. Contact details of authorised person	No authorised representative
6. Constancy of performance	System 1
7. Certifying body	MPA Stuttgart 0672 Certificate of Constancy of Performance No. 0672-CPR-0415
8. Certifying body	not relevant

**9. Declared performance**

**9.1 Product description**

The laminated veneer lumber is made from glued, dried beech veneer sheets with a width of up to H = 1850 mm and a length of up to L = 35 m.

Table 1: Structure of Board BauBuche S (beech LVL, parallel ply)

<b>Element thickness B not sanded – nominal dimension in mm</b>	<b>Element thickness B not sanded – nominal dimension in mm</b>	<b>Number pf plies</b>	<b>Structure</b>
21	19	7	IIIIII
21	20	7	IIIIII
24	22	8	IIIIIII
27	25	9	IIIIIIII
30	28	10	IIIIIIIII
33	30	11	IIIIIIIIII
33	31	11	IIIIIIIIII
36	34	12	IIIIIIIIIII
39	37	13	IIIIIIIIIIII
42	40	14	IIIIIIIIIIIII
45	43	15	IIIIIIIIIIIIII
48	46	16	IIIIIIIIIIIIIII
51	49	17	IIIIIIIIIIIIIIII
54	50	18	IIIIIIIIIIIIIIIII
54	52	18	IIIIIIIIIIIIIIIII
57	55	19	IIIIIIIIIIIIIIIIII
60	58	20	IIIIIIIIIIIIIIIIII
63	60	21	IIIIIIIIIIIIIIIIII
63	61	21	IIIIIIIIIIIIIIIIII
66	64	22	IIIIIIIIIIIIIIIIII
I	Ply parallel to long side		

Table 2: Structure of Board BauBuche Q (beech LVL, cross ply)

Element thickness B not sanded – nominal dimension in mm	Element thickness B sanded – nominal dimension in mm	Number of plies			Structure
		parallel	cross	total	
21	19	5	2	7	I-III-I
21	20	5	2	7	I-III-I
24	22	6	2	8	I-III-I
27	25	7	2	9	II-III-II
30	28	8	2	10	II-III-II
33	30	9	2	11	II-III-II
33	31	9	2	11	II-III-II
36	34	10	2	12	III-III-III
39	37	11	2	13	III-III-III
42	40	12	2	14	III-III-III
45	43	13	2	15	III-III-III
48	46	14	2	16	III-III-III
51	49	15	2	17	III-III-III
54	50	16	2	18	III-III-III
54	52	16	2	18	III-III-III
57	55	17	2	19	III-III-III
60	58	18	2	20	III-III-III
63	60	17	4	21	III-II-III-II-III
63	61	17	4	21	III-II-III-II-III
66	64	18	4	22	III-II-III-II-III

I     ply parallel to long side  
 -     ply at right angles to long side

### 9.2 Application

“Board BauBuche S“ and “Board BauBuche Q“ laminated veneer lumber according to EN 14374 are approved for use in all non-load bearing, load bearing and stiffening elements dimensioned and produced according to EN 1995-1-1 in conjunction with EN 1995-1-1/NA.

“Board BauBuche S“ and “Board BauBuche Q“ laminated veneer lumber are approved for use in service classes 1 and 2 according to EN 1995-1-1.

### 9.3 Declared strength, stiffness and density characteristics

Table 3: Characteristic strength and stiffness in N/mm<sup>2</sup>, and density in kg/m<sup>3</sup>

Load/stress type		Board BauBuche S laminated veneer lumber	Board BauBuche Q laminated veneer lumber	
		20 ≤ B ≤ 80	≤ 24 <sup>a)</sup>	27 ≤ B ≤ 66
<b>Characteristic strength</b>				
<b>Flatwise load</b>				
Bending	f <sub>m,0,flat,k</sub>	80	70	81
	f <sub>m,90,flat,k</sub>	---	34	21
Compression	f <sub>c,90,flat,k</sub>	10 <sup>c)</sup>	16 <sup>c)</sup>	
Shear	f <sub>v,0,flat,k</sub>	8	3,8	
<b>Edgewise load</b>				
Bending <sup>b)</sup>	f <sub>m,0,edge,k</sub>	75	54	59
	f <sub>m,90,edge,k</sub>	---	16	9
Tensile    to grain	f <sub>t,0,k</sub>	60	46	49
Tensile ⊥ to grain	f <sub>t,90,edge,k</sub>	1,5	15	8
Compressive    to grain	f <sub>c,0,k</sub>	57,5 <sup>c)</sup>	57 <sup>c)</sup>	62 <sup>c)</sup>
Compressive ⊥ to grain	f <sub>c,90,edge,k</sub>	14	40 <sup>c)</sup>	22 <sup>c)</sup>
Shear	f <sub>v,0,edge,k</sub>	8	7,8	

Load/stress type		Board BauBuche S laminated veneer lumber	Board BauBuche Q laminated veneer lumber	
Nominal thickness in mm		$20 \leq B \leq 80$	$\leq 24$ <sup>a)</sup>	$27 \leq B \leq 66$
<b>Characteristic stiffness</b>				
Modulus of elasticity	$E_{0,mean}$	16800	11800	12800
	$E_{0,05}$	14900	10900	11800
	$E_{90,mean}$	470	3500	2000
Shear modulus edgewise	$G_{v,0,edge,mean}$	760	820	
Shear modulus flatwise	$G_{v,0,flat,mean}$	850	430	
<b>Density</b>				
Mean density	$\rho_{mean}$	800	770	800
Charact. density	$\rho_k$	730		
<p>a) „Board BauBuche Q" with a nominal thickness of <math>\leq 24</math> mm according to appendix 2 must not be used in edge bending constructions.</p> <p>b) Values valid for <math>H \leq 300</math> mm. For <math>300 &lt; H \leq 1000</math> mm, the characteristic strength value must be multiplied with coefficient <math>k_h = (300/h)^{0,12}</math>. H is the total cross section in mm relevant for the determination of the bending strength.</p> <p>c) For use in service class 1, the compressive strength may be increased by factor 1.2.</p>				

#### 9.4 Fire safety

According to Commission Delegated Regulation (EU) 2017/2293, products „Board BauBuche S" and „Board BauBuche Q" are in class D-s2, d0.

For design charring rates for laminated veneer lumber, see EN 1995-1-2.

#### 9.5 Formaldehyde class

With regard to formaldehyde emissions, the laminated veneer lumber products „Board BauBuche S" and „Board BauBuche Q" conform to class E1, in line with the requirements laid down in EN 14374.

### 10. Declaration

The performance of the products specified in 1 and 2 corresponds to the declared performance in 9. This Declaration of Performance has been issued at the sole responsibility of the manufacturer named in 4.

Signed on behalf of the manufacturer:

Creuzburg, 27 July 2018



Ralf Pollmeier

Managing Director